

On the use of a single site approximation to describe correlation in pure metals

C.M. Chaves^{a,*}, A. A. Gomes^a, A. Troper^{a,b}

^a*Centro Brasileiro de Pesquisas Físicas, Rua Xavier Sigaud 150, Rio de Janeiro, 22290-180, RJ, Brazil*

^b*Centro Brasileiro de Pesquisas Físicas, Rua Xavier Sigaud 150, Rio de Janeiro, 22290-180, RJ, Brazil and Universidade do Estado do Rio de Janeiro, Rua São Francisco Xavier 524, Rio de Janeiro, RJ, Brazil*

Abstract

The magnetic properties of pure transition-like metals are discussed within the single site approximation, to take into account the electron correlation. The metal is described by two hybridized bands one of which includes the Coulomb correlation. Our results indicate that ferromagnetism follows from adequate values of the correlation and hybridization.

Key words: Ferromagnetic metal; Correlation; Single-site approximation;

PACS: 71.10.-w, 71.10.Fd, 71.20.Be

1. Introduction

The coherent potential approximation (CPA) has been largely used to provide a simple single site description of disordered alloys[?,1]. Another application of CPA procedures is the description of *pure* metals in presence of electron-electron correlations[2]. In this formulation, one describes the correlated electron by a spin and energy dependent effective self-energy which incorporates the effects of correlation. This self-energy is self-consistently determined by imposing the vanishing of the scattering T matrix associated to a given site which exhibits the full Coulomb interaction.

In our model, the metal has two non-degenerate bands, a and b . The first is a Hubbard-like narrow band with in-site interaction U , hybridized with the second one, b , a broader band. The Hamiltonian we adopt to describe pure metals is then

$$\mathcal{H} = \sum_{i,\sigma} \epsilon^a a_{i\sigma}^\dagger a_{i\sigma} + \sum_{i,j,\sigma} t_{ij}^a a_{i\sigma}^\dagger a_{j\sigma} + \sum_{i,j,\sigma} t_{ij}^b b_{i\sigma}^\dagger b_{j\sigma} \quad (1)$$

$$+ \sum_i U n_{i\uparrow}^{(a)} n_{i\downarrow}^{(a)} + \sum_{i,j,\sigma} (V_{ab} b_{i\sigma}^\dagger a_{j\sigma} + V_{ba}^+ a_{i\sigma}^\dagger b_{j\sigma}),$$

where $n_{i\sigma}^a = a_{i\sigma}^\dagger a_{i\sigma}$; σ denotes spin. t_{ij} denotes the tunneling amplitudes between neighboring sites i and j , in each band; ϵ^a is the center of the a -band. We follow Roth's

approach[2] to describe the electron-electron correlation through an effective Hamiltonian

$$\mathcal{H}_{eff} = \sum_{i,\sigma} \epsilon^a a_{i\sigma}^\dagger a_{i\sigma} + \sum_{i,j,\sigma} t_{ij}^a a_{i\sigma}^\dagger a_{j\sigma} + \sum_{i,j,\sigma} t_{ij}^b b_{i\sigma}^\dagger b_{j\sigma} \quad (2)$$

$$+ \sum_{i,\sigma} n_{i\sigma}^a \Sigma^\sigma + U n_{0\uparrow}^a n_{0\downarrow}^a + \sum_{i,j,\sigma} (V_{ab} b_{i\sigma}^\dagger a_{j\sigma} + h.c.)$$

$$- \sum_\sigma n_{0\sigma}^a \Sigma^\sigma,$$

where Σ^σ is the self-energy associated with electron-electron interaction. We recall that the main spirit of the method consists in replacing a translationally invariant problem, as defined by (1), by the alloy problem, defined by (2), where only the origin incorporates the Coulomb interaction. The effective Hamiltonian (2) still includes the difficulty of dealing with the Coulomb intra-atomic term at the origin and we have to resort to some approximation.

In the Green's function method[?,?], the equation of motion of a given Green's function generates higher order functions and we thus need a decoupling procedure. After some algebra[4] we end up with the following Green's functions:

$$G_{kk',\sigma}^a(w) = \frac{\delta_{kk'}}{w - \bar{\epsilon}_k^a - \Sigma^\sigma(w)}, \quad (3)$$

the Green's function of the bare b band,

$$G_{0,k\sigma}^b(w) = \frac{1}{w - \epsilon_k^b}, \quad (4)$$

and the Green's function of the renormalized b band

* Corresponding author. Tel: (05521) 2141-7285 fax: (05521) 2141-7400

Email address: cmch@cbpf.br (C.M. Chaves).

$$G_{kk\sigma}^b(w) = G_{0,k\sigma}^b(w) + G_{0,k\sigma}^b(w)VG_{kk,\sigma}^a(w)VG_{0,k\sigma}^b(w). \quad (5)$$

In these equations

$$\tilde{\epsilon}_k^a = \epsilon_k^a + \frac{V_{ab}^2(k)}{w - \epsilon_k^b}, \quad (6)$$

is the recursion relation of the renormalized a band; ϵ_k^a and ϵ_k^b denote the bare bands. The vanishing of the T-matrix gives a self-consistent equation for the self-energy:

$$\Sigma^\sigma = U < n_{0-\sigma}^a > + (U - \Sigma^\sigma)F^\sigma(w, \Sigma^\sigma)\Sigma^\sigma, \quad (7)$$

with

$$F^\sigma = \sum_k G_{kk,\sigma}^a \quad (8)$$

This is equivalent to an alloy analogy approximation, where the broadening correction[3] has been neglected.

Our self-consistent numerical results can describe a transition metal of the iron group (then $a \equiv d$ and $b \equiv s$) or some f electron compounds ($a \equiv f$ and $b \equiv s, p, d$).

In fig(1) we present the density of states (DOS) of the a -band for $U = 4$ and $V = 0.3$. In same units, the bare a band width is $W = 2$. The Fermi level is at $\epsilon_F = 0.45$. This gives $n_\uparrow^a = 0.475$ and $n_\downarrow^a = 0.390$ and thus a ferromagnetic moment of $m_a = 0.085$ is developed. The DOS here obtained exhibits a bimodal structure characterizing a Hubbard strongly correlated regime.

In fig (2) the real part of Σ^σ is displayed for $U = 4$ and $V = 0.3$. Σ^σ is a smooth function of energy and for this U differs considerably from the constant Hartree-Fock values ($\Sigma^\uparrow = 1.56, \Sigma^\downarrow = 1.90$).




Fig. 1. Density of states(DOS) of the a -band, up and down, for $U = 4$ and $V = 0.3$. The Fermi level is at $\epsilon_F = 0.45$. As a result $n_\uparrow^a = 0.475$ and $n_\downarrow^a = 0.390$, giving a ferromagnetic moment $m = 0.085$. The separation of the centers of the two subbands is U , as expected.

2. Summary

The traditional view of the origin of ferromagnetism in metals has been under intense scrutiny recently [5,6]). Conventional mean-field calculations favor ferromagnetism but




Fig. 2. Real part of the self-energy for up and down spins for $U = 4$ and $V = 0.3$.

corrections tend to reduce the range of validity of that ground state [6]. In this paper, using the single site approximation, we obtain ferromagnetic solution for a set of parameters (e.g. $U/W = 2$ and $V/W = 0.15$). A more complete study bringing up the interplay between U and V will be published elsewhere.

3. Acknowledgement

CMC and AT acknowledge the support from the brazilian agencies CNP_q and PCI/MCT .

References

- [1] H. Shiba, Progress Theo. Phys. 46 (1971)77 .
- [2] L.M.Roth, in AIP Conference Proceedings 18 Magnetism and Magnetic Materials, (1973) 668.
- [3] J. Hubbard, Proc. Royal Soc. A281 (1964) 401 .
- [4] A. N. Magalhães, M. A. Continentino, A Troper and A. A. Gomes, C.B.P.F., Notas Científicas XXIII 8 (1974) 127.
- [5] C. D. Batista *et al*, Phys. Rev. Letters 88 (2002) 187203 .
- [6] D. Vollhardt *et al*, Adv. Solid State Phys. 38 (1999) 383 .